This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

1. (Currently Amended) A process for the material recycling of LCDs, comprising mixing the LCDs with a composition that comprises a mixture of noble and non-noble metals, melting the mixture at a temperature range of 900 to 1700°C, cooling the resultant melt, breaking the cooled melt, and separating a part of the cooled melt that is enriched in the noble metals from the remaining part of the cooled melt.

- 2-3. (Cancelled)
- 4. (Previously Presented) A process according to Claim 1, wherein the LCD-containing mixture is melted at a temperature range of 1200 to 1400°C.
- 5. (Previously Presented) A process according to Claim 1, wherein the LCDs comprise electronic components.
  - 6. (Cancelled)
- 7. (Currently Amended) <u>A process according to Claim 1, further comprising</u> In a process for recovering noble metals from a composition comprising a mixture of noble and non-noble metals, which process comprises melting the mixture and adding furnace sand to bind the non-noble metals in the melted mixture, the improvement comprising replacing at least some of the furnace sand with LCDs.
  - 8. (Cancelled)
  - 9. (Currently Amended) <u>A process according to Claim 1, further</u>

comprising adding In a reductive melting process of metal containing compositions for the recovery of metals, which process comprises the addition of a carbon-containing product as a reducing agent to the melted mixture, the improvement comprising replacing at least some of the carbon-containing product with LCDs, wherein the plastic films present in the LCDs act as the reducing agent.

- 10. (Previously Presented) A process for the material recycling of LCDs, comprising thermally treating the LCDs in a rotary-tube furnace at a temperature of 1100 to 1300°C.
- 11. (Previously Presented) A process according to Claim 10, wherein the LCDs result in the formation of a protective film on the inner lining of the rotary-tube furnace.
- 12. (Currently Amended) A process according to Claim 10, further comprising In a process for increasing the lifespan of a chamotte lining in a rotary-tube furnace, which process comprises adding a silicate-containing compound to materials incinerated in into said furnace to form a protective film on the walls of said furnace, the improvement comprising replacing at least some of the silicate-containing compound with LCDs.

## 13-20. (Cancelled)

- 21. (Previously Presented) A process according to Claim 1, wherein the composition that comprises a mixture of noble and non-noble metals is an ore.
- 22. (Previously Presented) A process according to Claim 1, wherein the composition that comprises a mixture of noble and non-noble metals is a catalyst, electrical or electronic scrap or metal-containing sludge.
- 23. (New) A process according to Claim 1, wherein the proportion of LCDs in the mixture as a whole is 5 to 50% by weight.